

CC-7120**CARMASTER 2 PACK SPEED CLEARCOAT****PRODUCT DESCRIPTION**

Carmaster 2 Pack Speed Clearcoat is a fast drying two pack acrylic urethane clearcoat which provides good gloss and can be polished easily with minimum effort.

It is designed to be used on small areas or where the user is working in cooler conditions.

While *Carmaster* products have been tried and tested to be suitable for use in the harsh Australian conditions, they do not benefit from inclusion in the PROTEC® Autoguard Warranty program. If you require the assurance of a warranted product system, products from the *Paraglaze* range should be selected.

SUBSTRATES & PREPARATION

Carmaster 2 Pack Speed Clearcoat can be applied over:

- Clean and dust-free basecoat
- Fully cured 2 pack refinish clearcoats that have been degreased and sanded
- Sound OEM clearcoats that have been degreased and sanded


Substrates other than those stated above should be tested before use, to ensure that the performance of this product is suitable for its intended use.

The use of a clean tack rag is recommended to remove dust from the surface before topcoating.

PRODUCTS

<i>Carmaster 2 Pack Speed Clearcoat</i>	CC-7120
<i>Carmaster Normal Hardener</i>	CH-5200
<i>Carmaster Slow Hardener</i>	CH-5300
<i>Carmaster GP 2 Pack Reducer</i>	CS-3800
<i>Protec Flex Additive</i>	AA-5656

MIXING RATIO BY VOLUME



PRODUCT	PARTS
CC-7120	4
Carmaster Hardener	1
Carmaster GP 2 Pack Reducer	0 - 10%

FLEXIBILISATION


• AA-5656 *Protec* Flex Additive must be used at the following ratios when applying CC-7120 over plastics, to ensure proper flexibility of the clearcoat film:

PRODUCT	HARD	FLEXIBLE	HIGHLY FLEXIBLE
	PLASTICS	PLASTICS	PLASTICS
Uncatalysed CC-7120	-	5	2
AA-5656	Not Required	1	1

Always add AA-5656 to CC-7120 first and thoroughly mix → Then add hardener and reducer as per the normal recommendation above.


Note: Higher levels of AA-5656 will slow the drying time of CC-7120

POTLIFE



45 minutes at 25°C.

SPRAY VISCOSITY



16 - 18 seconds (DIN 4) at 25°C.

SPRAYGUN SETTINGS (*GRAVITY*)




SETUP	1.3 - 1.4 mm
SPRAY PRESSURE	
• HVLP / RP	1.8 - 2.2 bar
• CONVENTIONAL	3.0 - 3.5 bar

APPLICATION & FLASH OFF



Apply two even **full** coats



Allow 5 - 7 minutes flash off between coats at 25°C

DRYING TIMES



BAKE:

20 minutes at 60°C

Note: Temperature shown is metal temperature

I.R.:

14 - 18 minutes (short wave)

Will vary depending upon equipment. Refer to equipment supplier

TOTAL DRY FILM BUILD

50 - 60 µm

OVERCOAT / RECOAT



TIME:

Minimum of 8 hours after bake

Air dry overnight at 25°C

PREPARATION:

STARTLINE® P500 (dry) OR
Startline P800 (wet)

DE-NIBBING & POLISHING

Remove dirt if required using wet *Startline* abrasive, no more than P1500 grit, then cut and polish.

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.

HEALTH AND SAFETY

Please refer to Material Safety Data Sheets (MSDS) for full Health and Safety details, as well as product can labels.

Protec hardeners and activated products contain isocyanate and therefore particular safety precautions must be taken; please refer to MSDS for full health and safety details.

This product is for professional use only.
The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
Drying times quoted are average times at 25°C/77°F. Film thickness, humidity and shop temperature can all affect drying times.

**Protec Pty Ltd. 97–105 Bedford Street
Gillman, S.A. 5013 Australia**

EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

**Protec Pty Ltd. 5 Monahan Rd, Mt Wellington
Auckland, New Zealand**

EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096

Protec is a registered trademark of Protec Pty Ltd.
Startline is a registered trademark of PPG Industries Australia Pty Ltd.