CARMASTER

TECHNICAL DATA SHEET

CC-7120 CARMASTER 2 PACK SPEED CLEARCOAT

PRODUCT DESCRIPTION

Carmaster 2 Pack Speed Clearcoat is a fast drying two pack acrylic urethane clearcoat which provides good gloss and can be polished easily with minimum effort.

It is designed to be used on small areas or where the user is working in cooler conditions.

While Carmaster products have been tried and tested to be suitable for use in the harsh Australian conditions, they do not benefit from inclusion in the PROTEC® Autoguard Warranty program. If you require the assurance of a warranted product system, products from the Paraglaze range should be selected.

PRODUCTS

Carmaster 2 Pack Speed Clearcoat	CC-7120
Carmaster Normal Hardener	CH-5200
Carmaster Slow Hardener	CH-5300
Carmaster GP 2 Pack Reducer	CS-3800
Protec Flex Additive	AA-5656
Protec Heavy Duty Degreaser	AA-6822

SUBSTRATES & PREPARATION

Carmaster 2 Pack Speed Clearcoat can be applied over:

- Clean and dust-free basecoat
- Fully cured 2 pack refinish clearcoats that have been degreased and sanded
- Sound OEM clearcoats that have been degreased and sanded

Substrates other than those stated above should be tested before use, to ensure that the performance of this product is suitable for it's intended use.

The use of a clean tack rag is recommended to remove dust from the surface before topcoating.

MIXING RATIO BY VOLUME



PRODUCT	PARTS
CC-7120	4
Carmaster Hardener	1
CS-3800	0 - 10%

FLEXIBILISATION recommendation over page…

FLEXIBILISATION



AA-5656 *Protec* Flex Additive must be used at the following ratios when applying CC-7120 over plastics, to ensure proper flexibility of the clearcoat film:

PLASTIC TYPE	HARD PLASTICS	FLEXIBLE PLASTICS	HIGHLY FLEXIBLE PLASTICS
PRODUCT	**PARTS**		
Uncatalysed CC-7120	Not Required	5	2
AA-5656		1	1

Always add AA-5656 to CC-7120 first and thorughly mix → Then add hardener and reducer as per the normal recommendation above.

Note: Higher levels or AA-5656 will slow the drying time of CC-7120

POTLIFE



45 minutes at 25°C.

SPRAY VISCOSITY



16 - 18 seconds (DIN 4) at 25°C.

SPRAYGUN SETTINGS *(GRAVITY)*

SETUP 1.3 - 1.4 mm

SPRAY PRESSURE
- HVLP / RP: 1.8 - 2.2 bar
- CONVENTIONAL: 3.0 - 3.5 bar

APPLICATION & FLASH OFF *(at 25°C)*



- COATS: Apply two even **full** coats, to achieve film build
- FLASH OFF BETWEEN COATS: 5 - 7 minutes

DRYING TIMES

BAKE: 20 minutes at 60°C

Note: Temperature shown is metal temperature

I.R.: 14 - 18 minutes (short wave)

Will vary depending upon equipment. Refer to equipment supplier

TOTAL DRY FILM BUILD

50 - 60 µm

OVERCOAT / RECOAT

TIME: Minimum of 8 hours after bake
Air dry overnight at 25°C

PREPARATION: P500 (dry) OR P800 (wet)

DE-NIBBING & POLISHING

Remove dirt if required using wet abrasive, no more than P1500 grit, then cut and polish.

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.

HEALTH AND SAFETY

Refer to Safety Data Sheets (SDS) for full Health and Safety details, as well as product can labels.

Protec hardeners and activated products contain isocyanate and therefore particular safety precautions must be taken; please refer to SDS for full health and safety details.

This product is for professional use only.
The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
Drying times quoted are average times at 25°C/77°F. Film thickness, humidity and shop temperature can all affect drying times.

PPG Industries Pty Ltd, 14 McNaughton Road
Clayton, VIC 3168 Australia

EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

Protec Pty Ltd. 5 Monahan Rd, Mt Wellington
Auckland, New Zealand

EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096