CARMASTER

TECHNICAL DATA SHEET

CC-9550 CARMASTER GP 2 PACK CLEARCOAT

PRODUCT DESCRIPTION

Carmaster GP 2 Pack Clearcoat is a two pack acrylic urethane clearcoat designed for use as a general smash repair clearcoat.

It is formulated to give good gloss off the gun and is easy to polish and is designed to be used for multi panel and overall repainting.

While Carmaster products have been tried and tested to be suitable for use in the harsh Australian conditions, they do not benefit from inclusion in the PROTEC® Autoguard Warranty program. If you require the assurance of a warranted product system, products from the Paraglaze range should be selected.

PRODUCTS

Carmaster GP 2 Pack Clearcoat	CC-9550
Carmaster Normal Hardener	CH-5200
Carmaster Slow Hardener	CH-5300
Carmaster GP 2 Pack Reducer	CS-3800
Protec Flex Additive	AA-5656
Protec Heavy Duty Degreaser	AA-6822

SUBSTRATES & PREPARATION

Carmaster GP 2 Pack Clearcoat can be applied over:

- Clean and dust-free basecoat
- Fully cured 2 pack refinish clearcoats that have been degreased and sanded
- Sound OEM clearcoats that have been degreased and sanded

Substrates other than those stated above should be tested before use, to ensure that the performance of this product is suitable for it's intended use.

The use of a clean tack rag is recommended to remove dust from the surface before topcoating.

MIXING RATIO BY VOLUME



PRODUCT	PARTS
CC-9550	2
Carmaster Hardener	1
CS-3800	0 - 10%

FLEXIBILISATION recommendation over page…

FLEXIBILISATION



• AA-5656 *Protec* Flex Additive must be used at the following ratios when applying CC-9550 over plastics, to ensure proper flexibility of the clearcoat film:

PLASTIC TYPE	HARD PLASTICS	FLEXIBLE PLASTICS	HIGHLY FLEXIBLE PLASTICS
PRODUCT	**PARTS**		
Uncatalysed CC-9550	Not Required	5	2
AA-5656		1	1

Always add AA-5656 to CC-9550 first and thorughly mix → Then add hardener and reducer as per the normal recommendation above.

Note: Higher levels or AA-5656 will slow the drying time of CC-9550

POTLIFE



1 hour at 25°C.

SPRAY VISCOSITY



16 - 18 seconds (DIN 4) at 25°C.

SPRAYGUN SETTINGS *(GRAVITY)*

SETUP 1.3 - 1.4 mm

SPRAY PRESSURE
- HVLP / RP: 1.8 - 2.2 bar
- CONVENTIONAL: 3.0 - 3.5 bar

APPLICATION & FLASH OFF *(at 25°C)*



- COATS: Apply two even **full** coats
- FLASH OFF BETWEEN COATS: 5 - 7 minutes

BAKING TIME & TEMPERATURE

BAKE: 40 minutes at 60°C

Note: Temperature shown is metal temperature

I.R.: 14 - 18 minutes (short wave)

Will vary depending upon equipment. Refer to equipment supplier

TOTAL DRY FILM BUILD

50 - 60 µm

OVERCOAT / RECOAT

TIME: Minimum of 8 hours after bake
Air dry overnight at 25°C

PREPARATION: P500 (dry) OR P800 (wet)

DE-NIBBING & POLISHING

Remove dirt if required using wet *Startline* abrasive, no more than P1500 grit, then cut and polish.

EQUIPMENT CLEANING

After use, clean all equipment thoroughly with cleaning solvent or thinner.

HEALTH AND SAFETY

Refer to Safety Data Sheets (SDS) for full Health and Safety details, as well as product can labels.

Protec hardeners and activated products contain isocyanate and therefore particular safety precautions must be taken; please refer to SDS for full health and safety details.

This product is for professional use only.
The information given in this sheet is for guidance only. Any person using the product without first making further inquiries as to the suitability of the product for the intended purpose does so at his or her own risk and we can accept no liability for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
Drying times quoted are average times at 25°C/77°F. Film thickness, humidity and shop temperature can all affect drying times.

PPG Industries Pty Ltd, 14 McNauton Road
Clayton,VIC 3169 Australia

EMERGENCY RESPONSE NUMBER, Australia: 1800 883 254

Protec Pty Ltd. 5 Monahan Rd, Mt Wellington
Auckland, New Zealand

EMERGENCY RESPONSE NUMBER, New Zealand: 0800 000 096

Protec and the *Protec Logo* are registered trademarks of Protec Pty Ltd.
Startline is a registered trademark of PPG Industries Australia Pty Ltd.